

Black Specials, in a wallaby grain, is a performance vinyl coated upholstery designed for autotmotive and recreational vehicle seating applications.

### Industries & Markets

Automotive

### End-Use Applications

Aftermarket Upholstery

## **Physical Specifications**

Weight (CFFA-700d)	28 oz/lin yd [18.7 oz/yd²]
Weight, Metric (CFFA-700d)	849 g/lin m [619 g/m <sup>2</sup> ]
Width (CFFA-700a)	54 in. [137 cm]
Face Composition	PVC
Backing Description	Filament Polyester Knit
Roll Size	30 lin yd [27 lin m]
Emboss Level	Light
Shipping Weight/ Roll	54 lb [24 kg]

# Flame, Smoke & Toxicity

Meets or exceeds the following:	Cal Tech 117-2013 Sec 1
	• FMVSS-302
	UFAC Fabric, Class 1

## **Performance Features**

Protective Finish	Clear Vinyl
Adhesion #/in., min (CFFA-3)	3 Warp, 3 Fill
Tensile Strength #, min (CFFA-17)	75 Warp, 75 Fill
Tack Strength #, min (CFFA-14)	30 Warp, 30 Fill
Trap Tear Strength #, min (CFFA-16c)	20 Warp, 20 Fill
Wyzenbeek Abrasion (CFFA-1a)	6,000 Wirescreen (double rubs)
Blocking (CFFA-4 No. 1)	Pass
W-Flex - 25,000 cycles (CFFA-10)	Pass
Crocking Resistance - 20 cycles no stain (CFFA-7)	Pass
Cold Crack (CFFA-6a)	-10 °F [-23 °C]

# Note: Due to possible variances in your computer monitor, the colors and patterns displayed may vary slightly from the actual product. Customers should always obtain and compare actual samples before specifying.



World Headquarters OMNOVA Solutions Inc. 25435 Harvard Road Beachwood, OH 44122-6201 USA Phone: +1 216-682-7000 Email: upholstery@omnova.com Thailand Manufacturing Plant 111/7 Moo 2, T. Nikompattana

Amphur Nikompattana Rayong 21180, Thailand Phone: +011-66-38-897103 Fax: +011-66-38-637749

All OMNOVA products and services are offered and sold subject to the OMNOVA standard terms and conditions of sale agreement set forth at www.omnova.com

Trademarks are property of OMNOVA Solutions Inc. unless otherwise noted.  $\ensuremath{\textcircled{O}}$  2019 OMNOVA Solutions Inc.