

PreVaill Transit XMT Plus is our most durable vinyl coated fabric designed specifically for the North American market. It features the strength and durability of a non-expanded construction yet has the flexibility of an expanded construction for ease of fabrication of seats. Featuring the industry-leading **PreFixx** protective finish, it stands up to the most demanding requirements associated with mass tran. It is easiliy cleaned and can be disinfected without damage to the color of finish when the recommended cleaning instructions are followed. **PreVaill Transit XMT Plus** has been engineered to meet flame, smoke and toxicity requirements for the North American rail market and can be customized to meet agency-specific design, color and texture requirements.

Industries & Markets

- Transportation

End-Use Applications

- Public Transportation

Physical Specifications

Weight (CFFA-700d)	37.2 oz/lin yd [24.8 oz/yd ²]
Weight, Metric (CFFA-700d)	1,147 g/lin m [840 g/m ²]
Width (CFFA-700a)	54 in. [137 cm]
Face Composition	PVC
Backing Description	Polyester Spun Knit
Roll Size	40 lin yd [37 lin m]
Emboss Level	Medium
Shipping Weight/ Roll	93.6 lb [42 kg]

Flame, Smoke & Toxicity

- Meets or exceeds the following:
- Cal Tech 117-2013 Sec 1
 - FAR 25.853a & Appx F Part 1 (a)(1)(ii)
 - FMVSS-302
 - ASTM E662 Smoke

Performance Features

Protective Finish	PreFixx
Use	Indoor/Outdoor
QUV hours (minimum)	650
Adhesion #/in., min (CFFA-3)	3 Warp, 3 Fill
Tensile Strength #, min (CFFA-17)	110 Warp, 100 Fill
Tack Strength #, min (CFFA-14)	45 Warp, 40 Fill
Trap Tear Strength #, min (CFFA-16c)	20 Warp, 30 Fill
Wyzenbeek Abrasion (CFFA-1a)	50,000 Wirescreen (double rubs) 250,000 Cotton Duck (double rubs)
Blocking (CFFA-4 No. 2)	Pass
W-Flex - 25,000 cycles (CFFA-10)	Pass
Crocking Resistance - 20 cycles no stain (CFFA-7)	Pass
Fungal Resistance (ASTM-G-21)	Pass
Cold Crack (CFFA-6a)	-20 °F [-29 °C]
Compatible with Disinfectants	Yes. See Chem Resistance Tech Bulletin for more information.
Bleach-Safe	Yes, 10% Bleach Solution

Revision Date: 07.02.24

Note: Due to possible variances in your computer monitor, the colors and patterns displayed may vary slightly from the actual product. Customers should always obtain and compare actual samples before specifying.



North American Office

32125 Solon Road
Suite 150
Solon, Ohio 44139
USA
Phone: +1 216-682-7000
Email: upholstery@omnova.com

Thailand Manufacturing Plant

111/7 Moo 2, T. Nikompattana
Amphur Nikompattana
Rayong 21180, Thailand
Phone: +011-66-38-897103
Fax: +011-66-38-637749

All products and services are offered and sold subject to the standard terms and conditions of sale agreement set forth at www.omnova.com

Trademarks are property of OMNOVA - A Division of SURTECO unless otherwise noted.

©2024 OMNOVA - A Division of SURTECO